

# BENTOMAT® ST CERTIFIED PROPERTIES

CETCO® Bentomat® ST is a reinforced geosynthetic clay liner (GCL) consisting of a layer of sodium bentonite between a polypropylene woven geotextile and a polypropylene nonwoven geotextile, which are needle-punched together.

MATERIAL PROPERTY	TEST METHOD	TEST FREQUENCY	CERTIFIED VALUES
Woven Base Geotextile Mass/Area <sup>1</sup>	ASTM D5261	200,000 ft <sup>2</sup> (20,000 m <sup>2</sup> )	3.2 oz/yd <sup>2</sup> (108 g/m <sup>2</sup> ) min.
Nonwoven Cap Geotextile Mass/Area <sup>1</sup>	ASTM D5261	200,000 ft <sup>2</sup> (20,000 m <sup>2</sup> )	6.0 oz/yd <sup>2</sup> (203 g/m <sup>2</sup> ) min.
Bentonite Swell Index <sup>2</sup>	ASTM D5890	1 per 50 tonnes	24 mL/2g min.
Bentonite Fluid Loss <sup>2</sup>	ASTM D5891	1 per 50 tonnes	18 mL max.
Bentonite Mass/Area <sup>3</sup>	ASTM D5993	40,000 ft <sup>2</sup> (4,000 m <sup>2</sup> )	0.75 lb/ft <sup>2</sup> (3.7 kg/m <sup>2</sup> ) min.
Total Mass/Area <sup>3</sup>	ASTM D5993	40,000 ft <sup>2</sup> (4,000 m <sup>2</sup> )	0.81 lb/ft <sup>2</sup> (4.0 kg/m <sup>2</sup> ) min.
GCL Moisture Content	ASTM D5993	40,000 ft <sup>2</sup> (4,000 m <sup>2</sup> )	35% max.
GCL Grab Strength <sup>4</sup>	ASTM D6768	200,000 ft <sup>2</sup> (20,000 m <sup>2</sup> )	30 lbs/in (5.3 kN/m) min.
GCL Peel Strength	ASTM D6496	40,000 ft <sup>2</sup> (4,000 m <sup>2</sup> )	3.5 lbs/in (610 N/m) min.
GCL Hydraulic Conductivity <sup>5</sup>	ASTM D5887	250,000 ft <sup>2</sup> (25,000 m <sup>2</sup> )	5 x 10 <sup>-11</sup> m/s max.
GCL Index Flux <sup>5</sup>	ASTM D5887	250,000 ft <sup>2</sup> (25,000 m <sup>2</sup> )	1 x 10 <sup>-8</sup> m <sup>3</sup> /m <sup>2</sup> /s max.
GCL Hydrated Internal Shear Strength <sup>6</sup>	ASTM D6243	1,000,000 ft <sup>2</sup> (100,000 m <sup>2</sup> )	500 psf (24 kPa) typ.@ 200 psf (9.6 kPa)

Notes:

- <sup>1</sup> Geotextile property tests performed on the geotextile components before they are incorporated into the finished GCL product.
- <sup>2</sup> Bentonite property tests performed before the bentonite is incorporated into the finished GCL product.
- <sup>3</sup> Reported at 0% moisture content.
- <sup>4</sup> All tensile strength testing is performed in the machine direction using ASTM D6768.
- <sup>5</sup> Index flux and hydraulic conductivity testing with deaired distilled/deionized water at 80 psi (550 kPa) cell pressure, 77 psi (530 kPa) headwater pressure and 75 psi (515 kPa) tailwater pressure.
- <sup>6</sup> Peak values measured at 200 psf (9.6 kPa) normal stress for a specimen hydrated for 48 hours. Site-specific materials, GCL products, and test conditions must be used to verify internal and interface strength of the proposed design.